

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 3 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

**Amendment to the Claims:**

This listing of claims replaces all prior versions, and listings, of claims in the application:

1. (Currently Amended) A method of making a composite laminate material comprising:

interleaving

a plurality of first foils made from one or more of first metals and metal alloys, with

a plurality of second foils made from one or more of second metals and metal alloys suitable to react with the one or more of the first metal and metal alloys to produce a hard intermetallic compound, and wherein the one or more of the second metals and metal alloys are selected from the group consisting of aluminum and alloys of aluminum; and

reacting in situ under heat and pressure in the presence of atmospheric gases the plurality of first foils with the plurality of second foils so as to substantially completely react the one or more of the second metals and metal alloys with the one or more of the first metal and metal alloys, forming where each second metal foil had been a region of a hard intermetallic compound;

wherein a composite laminate material having (i) layers of the one or more of the first metals and metal alloys, interspersed with (ii) regions of the hard intermetallic compound, is made.

2. (Currently Amended) A method of making a composite laminate material comprising:

interleaving

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 4 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

a plurality of first foils made from one or more of first metals ~~[[or]]~~ and metal alloys from the group consisting of titanium, nickel, vanadium, iron and alloys and combinations of titanium, nickel, vanadium and iron, with

a plurality of second foils made from one or more of second metals and metal alloys from the group consisting of aluminum and alloys of aluminum; and

reacting under heat and pressure in the presence of atmospheric gases the plurality of first foils with the plurality of second foils so as to substantially completely react the one or more of the second metals and metal alloys with the one or more of the first metal and metal alloys, forming where each second metal foil had been a region of a hard intermetallic compound;

wherein a composite laminate material having (i) layers of the one or more of the first metals and metal alloys, interspersed with (ii) regions of ~~[[a]]~~ the hard intermetallic compound, is made.

3. (Currently Amended) The method of making a composite laminate material according to claim 1 or claim 2 wherein the reacting under heat and pressure comprises:

placing the interleaved pluralities of first foils and second foils under pressure:

raising the temperature of the pressured interleaved foils to (i) less than a melting point of the one or more of the second metals and metal alloys but (ii) sufficiently high so that, at pressure, solid state diffusion occurs between the interleaved foils, physically locking the foils in place;

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 5 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

further raising the temperature of the pressured, diffused, locked interleaved foils until all the one or more of the second metals and metal alloys are reacted with the one or more of the first metals and metal alloys to form [[an]] the intermetallic compound, this raising being done sufficiently slowly and under sufficient continuing pressure so that, despite the facts that the reacting proceeds with increasing difficulty and an ultimate high temperature reached is greater than a melting point of the one or more of the second metals and metal alloys, the one or more of the second metals and metal alloys remain initially locked in place and ultimately become reacted without squirting in liquid state from between the first foils; and

cooling the composite laminate material as is made from (i) layers of the one or more of the first metals and metal alloys, interspersed with (ii) regions of [[an]] the hard intermetallic compound, to room temperature;

wherein each of the placing, raising, further raising, and cooling transpires in the presence of atmospheric gases;

wherein the second foils become completely reacted with the first foils nonetheless that the temperature of liquefaction of the at least one of the second metals and metal alloys from which the second foils are made is exceeded in the process.

4. (Original) The method according to claim 1 or claim 2 wherein the interleaving is of a pluralities of first and second foils more numerous than ten.

5. (Currently Amended) The method according to claim 1 or claim 2 wherein the interspersing is of pluralities of first and

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 6 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

second foils having thicknesses in the range of ~~[[.1]]~~ 0.1 mm to 1 mm.

6. (Currently Amended) The method according to claim 1 or claim 2 wherein the interspersing is of pluralities of first and second foils having thicknesses less than ~~[[.2]]~~ 0.2 mm.

7. (Original) The method according to claim 1 or claim 2 wherein the maximum temperature of the reacting is in the range from 600-800°C.

8. (Original) The method according to claim 1 or claim 2 wherein the reacting under heat and pressure comprises:  
pressuring in a mechanical press.

9. (Original) The method according to claim 1 or claim 2 wherein the reacting under heat and pressure comprises:  
pressuring in a load frame.

10. (Original) The method according to claim 1 or claim 2 wherein the reacting under heat and pressure is under a maximum pressure in the range from 1-10 megapascals.

11-12. Canceled.

13. (Currently Amended) The method according to claim 1 or claim 2 wherein the ~~interspersing is of a plurality of first foils made from~~ one or more of the first metals and metal alloys ~~[[having]]~~ has a plane strain fracture toughness, in the state of the first metals and metal alloys that is assumed upon

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 7 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

completion of the method, of greater than  $40 \text{ MPa(m)}^{1/2}$   $[[\text{MPa}\sqrt{\text{m}}]]$ ,  
~~with a plurality of second metal foils made from~~ and the one or  
more of the second metals and metal alloys are suitable to  
compound with the first metal and metal alloys to produce  $[[\text{an}]]$   
the intermetallic compound having a Vickers microhardness of  
greater than  $400 \text{ kg/mm}^2$ .

14-15. Canceled.

16. (Original) The method according to claim 1 or claim 2  
wherein the laminating is of one or more tough first metals  
and metal alloys drawn from the group consisting of titanium,  
nickel, vanadium and iron, and combinations of titanium, nickel,  
vanadium, and iron.

17. Canceled.

18. (Original) The method according to claim 1 or claim 2  
producing the composite laminate material in a non-planar  
contour so as to improve its penetration resistance.

19. (Original) The method according to claim 1 or claim 2  
producing the composite laminate material in corrugated form so  
as to improve its penetration resistance.

20. Canceled.

21. (Currently Amended) The method according to claim 1 or  
claim 2,  $[[\text{producing}]]$  wherein the composite laminate material

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 8 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

[[having]] has a density between 3 and 4.5 grams per cubic centimeter.

22. (Currently Amended) The method according to claim 1 or claim 2, [[producing]] wherein the composite laminate material [[having]] has a density less than 6 grams per cubic centimeter.

23. (Currently Amended) The method according to claim 1 or claim 2

wherein the interleaving is of [[a]] the plurality of first foils and [[a]] the plurality of second foils under stress;

wherein the produced composite laminate material has residual internal stresses between its metal layers and its intermetallic regions.

24. (Original) The composite laminate material produced by the method according to claim 1 or claim 2 adapted for use as armor.

25. (Original) The method according to claim 1 or claim 2 wherein the interleaving is of metal layers that are in a three-dimensional, non-planar, contour;

wherein the intermetallic regions are in a three-dimensional, non-planar, contour congruent with the contour of the metal layers;

whereby the produced composite laminate material is in a three-dimensional, non-planar, contour.

26. (Original) The method according to claim 1 or claim 2

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 9 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

wherein the interleaving is of metal layers that are in a corrugated contour; and

wherein the intermetallic regions are in a corrugated contour congruent with the contour of the metal layers;

whereby the produced composite laminate material is in a corrugated contour.

27. (Original) The method according to claim 1 or claim 2 wherein the interleaving is of metal layers that are both greater than 10 in number and larger than 100 cm<sup>2</sup> in area.

28. (Currently Amended) The method according to claim 1 or claim 2

wherein the composite laminate material produced is characterized in that its metal layers have a toughness, in the state of the metals and metal alloys that is assumed upon completion. of the method, of greater than 40 MPa (m)<sup>1/2</sup> [[MPa√m]].

29. (Original) The method according to claim 1 or claim 2 wherein the composite laminate material produced is characterized in that its regions of intermetallic material have a Vickers microhardness of greater than 400 kg/mm<sup>2</sup>.

30-40. Canceled.

41. (Original) The method according to claim 1 or claim 2 wherein the interleaving is of metal layers that are of differing thickness.

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 10 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

42. (Original) The method according to claim 1 or claim 2 wherein the interleaving is of intermetallic regions that are of differing thickness.

43. (Original) The method according to claim 1 or claim 2 wherein the interleaving is of [[a]] the plurality of first foils and [[a]] the plurality of second foils under stress;

wherein the produced composite laminate material has such residual internal stresses between the metal layers and intermetallic regions as do serve to more substantially deflect a penetrating projectile from off its axis of impact than would be the case for the same penetrating projectile without the residual internal stresses.

44-49. Canceled

50. (New) A method of making a composite laminate material, comprising:

interleaving (1) a plurality of first foils made from one or more of first metals and metal alloys, with (2) a plurality of second foils made from one or more of second metals and metal alloys suitable to react with the one or more of the first metal and metal alloys to produce a hard intermetallic compound; and

reacting in situ under heat and pressure in the presence of atmospheric gases the plurality of first foils with the plurality of second foils so as to substantially completely react the one or more of the second metals and metal alloys with the one or more of the first metal and metal alloys to form



Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 11 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

where each second metal foil had been a region of a hard inter-metallic compound,

wherein the maximum temperature of the reacting is in the range from 600-800°C.

51. (New) A method of making a composite laminate material, comprising:

interleaving (1) a plurality of first foils made from one or more of first metals and metal alloys, with (2) a plurality of second foils made from one or more of second metals and metal alloys suitable to react with the one or more of the first metal and metal alloys to produce a hard intermetallic compound; and

reacting in situ under heat and pressure in the presence of atmospheric gases the plurality of first foils with the plurality of second foils so as to substantially completely react the one or more of the second metals and metal alloys with the one or more of the first metal and metal alloys to form where each second metal foil had been a region of a hard inter-metallic compound,

wherein the one or more of the first metals and metal alloys has a plane strain fracture toughness, in the state of the first metals and metal alloys that is assumed upon completion of the method, of greater than  $40 \text{ MPa(m)}^{1/2}$ , and the one or more of the second metals and metal alloys are suitable to compound with the first metal and metal alloys to produce the intermetallic compound having a Vickers microhardness of greater than  $400 \text{ kg/mm}^2$ .

52. (New) A method of making a composite laminate material, comprising:

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 12 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

interleaving (1) a plurality of first foils made from one or more of first metals and metal alloys, with (2) a plurality of second foils made from one or more of second metals and metal alloys suitable to react with the one or more of the first metal and metal alloys to produce a hard intermetallic compound; and

reacting in situ under heat and pressure in the presence of atmospheric gases the plurality of first foils with the plurality of second foils so as to substantially completely react the one or more of the second metals and metal alloys with the one or more of the first metal and metal alloys to form where each second metal foil had been a region of a hard intermetallic compound,

wherein the composite laminate material has a density between 3 and 4.5 grams per cubic centimeter.

53. (New) A method of making a composite laminate material, comprising:

interleaving (1) a plurality of first foils made from one or more of first metals and metal alloys, with (2) a plurality of second foils made from one or more of second metals and metal alloys suitable to react with the one or more of the first metal and metal alloys to produce a hard intermetallic compound; and

reacting in situ under heat and pressure in the presence of atmospheric gases the plurality of first foils with the plurality of second foils so as to substantially completely react the one or more of the second metals and metal alloys with the one or more of the first metal and metal alloys to form where each second metal foil had been a region of a hard intermetallic compound,

Applicant : Kenneth Vecchio  
Serial No. : 10/074,057  
Filed : February 11, 2002  
Page : 13 of 21

Attorney's Docket No.: 15670-  
032002 / SD1998-065-2

wherein the composite laminate material has a density less  
that 6 grams per cubic centimeter.